



EMERALD AND DIAMOND RING, BY VAN CLEEF & ARPELS, N.Y.

Platinum 10% Iridium and yellow gold 750.

Set with 1 fine, octagonal Colombian emerald of ca. 10.00 ct, minimally oiled, minimal traces of wear, within a brilliant-cut diamond surround totalling ca. 2.10 ct, the ring shoulders decorated with brilliant-cut diamonds of ca. 0.50 ct. Signed Van Cleef & Arpels N.Y., no. 40660. Size ca. 57.

[CatItem.ArtText.Text502]

CHF 40 000 / 60 000

€ 41 240 / 61 860

Koller Auktionen - Lot 2285*

A189 Joaillerie (Part 2) - mercredi 26 juin 2019, 14h00



Koller Auktionen - Lot 2285*
A189 Joaillerie (Part 2) - mercredi 26 juin 2019, 14h00



SSEF
 SCHWEIZERISCHES GEMMOLOGISCHES INSTITUT
 SWISS GEMMOLOGICAL INSTITUTE
 INSTITUT SUISSE DE GEMMOLOGIE



Test Report No. 102807

on the authenticity of the following gemstone,
 set in a ring with diamonds

Total weight:	12.1 grams (including setting and diamonds)
Shape & cut:	octagonal, step cut
Measurements:	approximately 15.75 x 12.70 x 7.00 mm
Estimated weight:	approximately 10 ct. (see also line declared weight in the comments)
Colour:	green of medium strong saturation
Identification:	EMERALD (variety of natural beryl)
Comments:	The analysed properties confirm the authenticity of this transparent emerald. Indications of clarity modification. Minor amount of oil in fissures at the time of testing. Origin: Colombia The estimated weight is in accordance with the declared weight of 10.24 ct.

Correspondence table for filler quantification

Filler	Minor amount of filler in fissures	Moderate amount of filler in fissures	Significant amount of filler in fissures	Filler in cavities
Referential system	F1	F2	F3	G1 G2 G3

Important Note: The conclusions on this Test Report reflect our findings at the time it is issued. A gemstone or pearl can be modified and/or enhanced at any time. Therefore, the SSEF can at any time reassess whether the gemstone or pearl is in accordance with this Test Report. A setting may limit complete analysis of a gemstone or a pearl, thus all conclusions are given as far as the setting permits. The authenticity and colour authenticity of additional diamonds, gemstones, and pearls in the setting have not been tested. The indicated estimated weight is only approximate and may differ from the exact weight of the gemstone/pearl when unset. Only the Test Report with the valid original signature, embossed stamp and Proof Tag™ label affixed onto the surface of the laminated Test Report is a valid document. PDF scans and copies of a Test Report are not legally binding. See terms and conditions on reverse side and www.ssef.ch/terms-conditions. © This report is copyright of SSEF.

SWISS GEMMOLOGICAL INSTITUTE - SSEF

Basel, 20 September 2018 mnr



S. Hänsel, MSc, FGA

Report authentication log on to www.myssef.ch





Dr. M. S. Krzernicki, FGA

Antschengsben 26, CH-4051 Basel, Switzerland Tel. +41 61 262 06 40 Fax + 41 61 262 06 41 admin@ssef.ch www.ssef.ch